

## FELDSPAR K200BL

### FELDSPAR

### BANGLÉN, THAILAND

### Granulometric Data & Physical Characteristics

Mean values. These do not represent a specification.

#### FELDSPAR K200BL

% Non-fused @ 1220°C	%			77	
Specific Gravity	g/cm <sup>3</sup>			2.6	
Moisture Content	%			0.2	ASTM-C-566
Fired Colour @ 1220°C			L	70	Spectrophotometer -KONICA MINOLTA
			a	2	
			b	3	

% Retained on Individual Sieves	%	100 Mesh	150 Micron	-	Wet Sieve
	%	200 Mesh	75 Micron	0.5	
	%	325 Mesh	45 Micron	12	
PSD by Malvern (% finer)	µm		20 Micron	57	Laser Particle Size Analyze
	µm		10 Micron	38	
	µm		5 Micron	25	
	µm		2 Micron	11	
	µm		1 Micron	5	
	µm		0.5 Micron	0	
Median Particle Size	µm		D50	16	

### Chemical Analysis (XRF) %

Mean values. These do not represent a specification.

#### FELDSPAR K200BL

K <sub>2</sub> O	%	11.2
Na <sub>2</sub> O	%	2.8
SiO <sub>2</sub>	%	67.5
Al <sub>2</sub> O <sub>3</sub>	%	17.7
Fe <sub>2</sub> O <sub>3</sub>	%	0.1
CaO	%	0.2
TiO <sub>2</sub>	%	0
MgO	%	0
LOI	%	0.4

### Availability

Pack Size: 50KG PP PLASTIC BAGS

1000 KG JUMBO BAGS

Shipping Point: BANGKOK, THAILAND

### For Product Information & Customer Service

Sibelco, Thailand

PHONE: +66 2019 9900-8 FAX: + 66 2019 9912-13

[www.sibelcoasia.com/enquiries](http://www.sibelcoasia.com/enquiries)

The technical data presented here is for marketing purposes only and is not contractually binding, the data herein is determined using Sibelco standard test methods. Since the product is based upon a naturally occurring material, we reserve the right to change this data when necessary. Safety information accompanying this product is available in the form of an SDS. All sales are undertaken strictly in accordance with our "General Conditions of Sale", available upon request, or by a written sales agreement duly signed by us.

FELDSPAR\_K200BL\_TDS\_BGL\_TH\_MAY21\_EN\_1.00